

Multi layer Greenhouse cover film

Type : SUNCOVER CLEAR

C 643

Film usage	:	Greenhouse cover
Width	:	Up to 15 meters
Thickness	:	120 micron
Length	:	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	22.5
	TD	“	MPa	22.0
Elongation at break	MD	“	%	550
	TD	“	%	650
Tear resistance	MD	ASTM D1922	Gr./mm.	9000
	TD	“	Gr./mm	10000
Falling dart drop impact		ASTM D-1709	Gram	600

Light transmission in PAR	%	90
Diffused light tr. in PAR	%	20

Typical values

Issued – 1/2012