

Multilayer cover film

Type : OVERWINTER CLEAR PLUS

C 824

Film usage	:	Low tunnel cover
Width	:	Up 5 meters
Thickness	:	50 micron
Length	:	As required

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	35.0
	TD	"	MPa	40.0
Elongation at break	MD	"	%	550
	TD	"	%	650
Tear resistance	MD	ASTM D1922	gr./mm.	12000
	TD	"	gr./mm	20000
Falling dart drop impact		ASTM D-1709	gram	400

Light transmission in PAR	%	ASTM D-1003	90
Diffused light in PAR	%	"	20

Typical values

Issued - 2/2018

Ginegar Plastic Products Ltd

Kibbutz Ginegar 3658000, Israel

T. +972 46544222) F. +972 46547947

export@ginegar.co.il) www.ginegar.com



Knowing your needs
empowering your growth