

## Bio Degradable Mulch film

**Type : EcoGar Black**

**C 807**

Film usage	:	Mulch film
Width	:	As required
Thickness	:	12 / 15 / 18 micron
Length	:	As required

The product complies with standards – EN 13432 / EN 17033 / ASTM D6400

		Test method	Units	Values
Tensile strength at break	MD	ASTM D-882	MPa	22
	TD	“	MPa	22
Elongation at break	MD	“	%	400
	TD	“	%	400
Tear resistance	MD	ASTM D1922	gr./mm.	7500
	TD	“	gr./mm.	7500
Falling dart drop impact		ASTM D-1709	gram	200

Minimum values

Light transmission in PAR	%	ASTM D-1003	< 1
---------------------------	---	-------------	-----

Remarks : Biodegradation happens in the soil, bury mulch residues at crop end as soon as possible.

Please refer to lay-out instructions in the brochure.

Issued – 4/2019

**Ginegar Plastic Products Ltd**

Kibbutz Ginegar 3658000, Israel

T. +972 46544222 ) F. +972 46547947

export@ginegar.co.il ) [www.ginegar.com](http://www.ginegar.com)



Knowing your needs  
empowering your growth